3M PTFE Skived Film Tape 5480 • 5481



konport.pl tasmy@konport.pl



D	2MATM DEEE CL.: 1 P.1		01 (
Product Description	3M [™] PTFE Skived Film Tape 5480 and 5481 tapes offer an extremely low coefficient of friction which, in combination with a pressure sensitive silicone adhesive, creates a smooth, non-stick surface over a variety of substrates to assist in the movement of web materials in many types of roll-wrap applications				
Skived PTFE (polytetrafluoroethylene)	Silicone	Gray	36 yds. (32.9 m)		
Typical Physical	Note: The following techni	ical information and (data should be con	sidered representative	
Properties	or typical only and should	not be used for specif	ication purposes.	-	
				ASTM Test Method	
	3M tape 5480			ASIM lest Method	
	3M tape 5480 Adhesion to Steel:	20 oz./in. width (22	N/100 mm)	D-3330	
	•	20 oz./in. width (22 26 lbs./in. width (46	,		
	Adhesion to Steel: Tensile Strength: Elongation at Break:	26 lbs./in. width (46 140%	,	D-3330	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm)	,	D-3330 D-3759	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm)	1 N/100 mm)	D-3330 D-3759 D-3759	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm)	1 N/100 mm)	D-3330 D-3759 D-3759 D-3652	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm)	1 N/100 mm)	D-3330 D-3759 D-3759 D-3652	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness: Temperature Use Range:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm)	1 N/100 mm) to 260°C)	D-3330 D-3759 D-3759 D-3652	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness: Temperature Use Range: 3M tape 5481	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm) -65° to 500°F (-54°	1 N/100 mm) to 260°C) N/100 mm)	D-3330 D-3759 D-3759 D-3652 D-3652	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness: Temperature Use Range: 3M tape 5481 Adhesion to Steel:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm) -65° to 500°F (-54° 32 oz./in. width (35	1 N/100 mm) to 260°C) N/100 mm)	D-3330 D-3759 D-3759 D-3652 D-3652 D-3652	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness: Temperature Use Range: 3M tape 5481 Adhesion to Steel: Tensile Strength:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm) -65° to 500°F (-54° 32 oz./in. width (35 59 lbs./in. width (10	1 N/100 mm) to 260°C) N/100 mm)	D-3330 D-3759 D-3759 D-3652 D-3652 D-3652 D-3330 D-3759	
	Adhesion to Steel: Tensile Strength: Elongation at Break: Backing Thickness: Total Tape Thickness: Temperature Use Range: 3M tape 5481 Adhesion to Steel: Tensile Strength: Elongation at Break:	26 lbs./in. width (46 140% 2.0 mils (0.05 mm) 3.7 mils (0.09 mm) -65° to 500°F (-54° 32 oz./in. width (35 59 lbs./in. width (10 290%	1 N/100 mm) to 260°C) N/100 mm)	D-3330 D-3759 D-3759 D-3652 D-3652 D-3652 D-3330 D-3759 D-3759	

Features

- Skived 3M[™] PTFE Film Tapes are more conformable than typical extruded PTFE film tapes.
- Provides excellent chemical resistance except to organic solvents. **Note:** The silicone adhesive will be attacked by commercial organic solvents and so are not recommended for applications requiring organic resistance.
- Silicone adhesive provides clean removal from a variety of surfaces.
- Non-stick PTFE film provides an exceptionally slick surface for easy clean-up.

3M[™] PTFE Skived Film Tape

5480• 5481

Application Ideas	• Easy-release surface provided by wrapping rollers, plates, belts, etc. where build- up of sticky materials and inks can occur.			
	• Shielding and protecting against chemicals.			
	• Mold release for composite or metal bonding.			
	• High temperature wire bundling and harnessing.			
	• High strength and abrasion resistance reduce friction between surfaces, minimizing squeak and noise.			
	• Wide temperature range for performance on heated machinery and equipment.			
	CAUTION: When PTFE film tape is exposed to temperatures above 600°F (316°C), small quantities of hazardous vapors may be released. INHALATION OF THESE VAPORS MAY BE HARMFUL OR MAY CAUSE RESPIRATORY TRACT IRRITATION. Do not heat or expose PTFE film tape to temperatures above 600°F (316°C).			
Storage	Store under normal conditions of 60° to 80° F (16° to 27° C) and 40 to 60% R.H. i the original carton.			
Shelf Life	To obtain best performance, use this product within 24 months from date of manufacture.			
Technical Information	The technical information, recommendations and other statements contained in this document are bas upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.			
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the u and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product a determining whether it is fit for a particular purpose and suitable for user's method of application.			
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.			
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.			
	(ISO 9001:2000)			
	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.			



Industrial Business Industrial Adhesives and Tapes Division 3M Center, Building 220-3S-06 800-362-3550 • 577-369-2923 (Fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer

3M is a trademark of 3M Company. Printed in U.S.A. ©3M 2016