



# VHB™ Thin Foam Tape

5906, 5907, 5908, 5909



konport.pl  
tasmy@konport.pl



## Technical Data

April, 2014

**Product Description** 3M™ VHB™ Thin Foam Tapes 5906, 5907, 5908 and 5909 are thin foam tapes with pressure sensitive adhesive on both sides and are used for bonding a wide range of materials, including many paints and lower surface energy plastics in addition to metals and other plastics. The foam is conformable to increase contact with the surfaces. This tape is similar to other products in the 3M™ VHB™ Tape 5952 family except thickness.

|                             |                                   |                                    |
|-----------------------------|-----------------------------------|------------------------------------|
| <b>Product Construction</b> | <b>Adhesive:</b> Modified Acrylic |                                    |
|                             | <b>Thickness:</b>                 |                                    |
|                             | <b>5906</b>                       | 0.006 in (0.15 mm)                 |
|                             | <b>5907</b>                       | 0.008 in (0.20 mm)                 |
|                             | <b>5908</b>                       | 0.010 in (0.25 mm)                 |
|                             | <b>5909</b>                       | 0.012 in (0.3 mm)                  |
|                             | <b>Thickness Tolerance:</b>       | +/- 15%                            |
|                             | <b>Density:</b>                   | 45 lb/ft³ (720 kg/m³)              |
|                             | <b>Liner:</b>                     | 0.003 in (0.08 mm) clear polyester |
|                             | <b>Tape Color:</b>                | Black                              |
|                             |                                   |                                    |

## Typical Physical Properties and Performance Characteristics

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

|  |             |                                      |
|--|-------------|--------------------------------------|
| <b>Peel Adhesion:</b><br>(stainless steel) | <b>5906</b> | 10 lb/inch (175 N/100 mm)            |
|  | <b>5907</b> | 10 lb/inch (175 N/100 mm)            |
|  | <b>5908</b> | 12 lb/inch (210 N/100 mm)            |
|  | <b>5909</b> | 12 lb/inch (210 N/100 mm)            |
| <b>Static Shear:</b><br>(stainless steel)  | 22°C        | 1000 g/0.5 sq in (holds 10,000 min.) |
|  | 70°C        | 500 g/0.5 sq in (holds 10,000 min.)  |
| <b>Solvent Resistance:</b>                 |             | High                                 |
| <b>Temperature Resistance:</b>             |             |                                      |
| <b>Short Term:</b> (minutes, hours)        |             | 121°C (250°F)                        |
| <b>Long Term:</b> (days, weeks)            |             | 82°C (180°F)                         |

## Available Sizes

|                                     |  |                        |
|-------------------------------------|--|------------------------|
| <b>Standard Length:</b>             |  | 65.8 meters (72 yards) |
| <b>Minimum Length:</b>              |  |                        |
| 1 inch (25.4 mm) to 8 inch (203 mm) |  | 329 meters (360 yards) |
| All other                           |  | 165 meters (180 yards) |
| <b>Minimum Width:</b>               |  | 12.7 mm (0.5 inch)     |
| <b>Maximum Width:</b>               |  | 1170 mm (46 inch)      |
| <b>Slitting Tolerance:</b>          |  | +/- 0.8 mm (1/32 in)   |
| <b>Core Size (ID):</b>              |  | 76.2 mm (3.0 in)       |

# 3M™ VHB™ Thin Foam Tape

5906, 5907, 5908, 5909

---

|                               |   |
|-------------------------------|---|
| <b>Application Guidelines</b> | For maximum bond strength the surfaces should be thoroughly cleaned with a 50:50 mixture of isopropyl alcohol and water. Consult manufacturers directions for use and precautions when using cleaning solvents. Ideal tape application is accomplished when temperature is between 21°C and 38°C (between 70°F and 100°F) and the bond is allowed to dwell 72 hours. Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended. |
|-------------------------------|---|

---

|                   |   |
|-------------------|---|
| <b>Shelf Life</b> | 24 Months from date of shipment when stored at 4°C to 38°C (40°F to 100°F) and 0-95% relative humidity. The optimum storage conditions are 22°C (72°F) and 50% relative humidity. |
|-------------------|---|

---

|                              |  |
|------------------------------|--|
| <b>Technical Information</b> | The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. |
|------------------------------|--|

---

|                    |  |
|--------------------|--|
| <b>Product Use</b> | Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. |
|--------------------|--|

---

|                         |   |
|-------------------------|---|
| <b>Limited Warranty</b> | 3M warrants for 24 months from the date of shipment that 3M™ VHB™ Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. This limited warranty does not cover damage resulting from the use or inability to use 3M™ VHB™ Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures. AN APPLICATION WARRANTY EXPRESSLY APPROVED AND ISSUED BY 3M IS AN EXCEPTION. THE CUSTOMER MUST APPLY FOR A SPECIFIC APPLICATION WARRANTY AND MEET ALL WARRANTY AND PROCESS REQUIREMENTS TO OBTAIN AN APPLICATION WARRANTY. CONTACT 3M FOR MORE INFORMATION ON APPLICATION WARRANTY TERMS AND CONDITIONS. |
|-------------------------|---|

---

|   |  |
|---|--|
| <b>Limitation of Remedies and Liability</b> | If the 3M™ VHB™ Tape is proved to be defective within the warranty period stated above. THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M™ VHB™ TAPE. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. |
|---|--|



This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



## Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (Fax)  
www.3M.com/VHB



Recycled Paper  
40% pre-consumer  
10% post-consumer

3M and VHB are trademarks of 3M.  
Printed in U.S.A.  
©3M 2014 (4/14)