



Technical Data Sheet

3M™ Adhesive Transfer Tape 9482PC

Product Description

Finite Element Analysis (FEA) data is available for this product at: [3m.com/FEA](https://www.3m.com/FEA)

This 3M™ Adhesive Transfer Tape with 3M™ Adhesive 350 is a modified acrylic adhesive ideal for very high-bond strength to many surfaces. It has excellent chemical resistance and bold strength even at elevated temperatures. This tape is offered with a fiber reinforced adhesive which is important for roll stability in narrow widths. Tapes using adhesive 350 are designed for temperature exposure to 450°F (232°C) for short periods of time and up to 300°F (149°C) over long time frames. This adhesive is a good choice for applications which require adhesion to Low Surface Energy plastics, powder coatings and oily metals.

General Information

- Excellent bond to metal and high surface energy plastics.
- Outstanding temperature and chemical resistance.
- Two adhesive thicknesses: 2 mil for thin profile labels and 5 mil for rougher surfaces.
- Available on various liners for specialized processing:
 - 55# Densified Kraft for rotary die-cutting
 - 62# Polycoated Kraft for steel rule die-cutting
 - 83# Polycoated Kraft for lay flat applications
 - 78# Extensible Kraft for conformable applications

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	Additional Information
Adhesive Type	Acrylic	
Liner	62# Polycoated Kraft	
Liner Thickness	0.11 mm	
Total Tape Thickness (mil)	2 mil	

View

Test Method: ASTM D3652

Total Tape Thickness (mm)

0.05 mm

View

Test Method: ASTM D3652

Liner Print

None

Liner Thickness

4.2 mil

Dispenser Selection

For assistance in helping you determine the best dispenser for your application, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

Typical Performance Characteristics

Property

Values

Additional Information

Short Term Temperature Resistance

450 °F

Short Term Temperature Resistance

232 °C

Long Term Temperature Resistance

121 °C

Minimum Long Term Temperature Resistance

-40 °C

Long Term Temperature Resistance


250 °F

Minimum Long Term Temperature Resistance

-40 °F

Static Shear

10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear


10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear

10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear


10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear

10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear


10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear

10000 min

View 

Notes: 1in x 1in size; test terminated after 10,000 minutes

180° Peel Adhesion

6.5 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Painted Metal

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

60 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Painted Metal

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

7.1 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polycarbonate (PC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

65 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polycarbonate (PC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

6.5 N/cm

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Acrylic (PMMA)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

60 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Acrylic (PMMA)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

7.1 N/cm

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Epoxy

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

65 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Epoxy

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

7.1 N/cm

View 

Test Method: ASTM D3330


Dwell/Cure Time: 72.0

Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

65 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

5.5 N/cm

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polyvinyl chloride (PVC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

50 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polyvinyl chloride (PVC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

6.5 N/cm

View 

Test Method: ASTM D3330


Dwell/Cure Time: 72.0
Dwell Time Units: hr

Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

60 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

9.8 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Glass

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

90 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Glass

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

3.3 N/cm





View 

Test Method: ASTM D3330

Dwell/Cure Time: 72.0
Dwell Time Units: hr
Temp C: 23C




Temp F: 72F
Environmental Condition: 50%RH
Substrate: High Density Polyethylene (HDPE)

Notes: 12 in/min (300 mm/min)

<div>180° Peel Adhesion</div> <div>30 oz/in</div> <div>View </div>	
<div>Test Method: ASTM D3330</div> <div>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: High Density Polyethylene (HDPE)</div> <div>Notes: 12 in/min (300 mm/min)</div>	
<div>180° Peel Adhesion</div> <div>3.8 N/cm</div> <div>View </div>	
<div>Test Method: ASTM D3330</div> <div>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Low Density Polyethylene (LDPE)</div> <div>Notes: 12 in/min (300 mm/min)</div>	
<div>180° Peel Adhesion</div> <div>35 oz/in</div> <div>View </div>	
<div>Test Method: ASTM D3330</div> <div>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Low Density Polyethylene (LDPE)</div> <div>Notes: 12 in/min (300 mm/min)</div>	
<div>180° Peel Adhesion</div> <div>5.5 N/cm</div> <div>View </div>	
<div>Test Method: ASTM D3330</div> <div>Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F</div>	

Environmental Condition: 50%RH
Substrate: Aluminum

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion
50 oz/in
View 
Test Method: ASTM D3330
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Aluminum
Notes: 12 in/min (300 mm/min)
180° Peel Adhesion
8.7 N/cm
View 
Test Method: ASTM D3330
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel
Notes: 12 in/min (300 mm/min)
180° Peel Adhesion
80 oz/in
View 
Test Method: ASTM D3330
Dwell/Cure Time: 72.0 Dwell Time Units: hr Temp C: 23C Temp F: 72F Environmental Condition: 50%RH Substrate: Stainless Steel
Notes: 12 in/min (300 mm/min)
Liner Release
40 g/in

Available Sizes

Property
Values
Additional Information


Note

Subject to Minimum Order Requirements


Standard Roll Length
60 yd

Maximum Length
54.9 m
View 


Width: 1/8 in to 3/8 in width

Maximum Length
60 yd
View 


Width: 1/8 in to 3/8 in width

Maximum Length
165 m
View 


Width: 3/8 in to 1/2 in width

Maximum Length
180 yd
View 

Width: 3/8 in to 1/2 in width

Maximum Length
329 m
View 

Width: 1/2 in to 1 in widths


Maximum Length
360 yd
View 

Width: 1/2 in to 1 in widths

Maximum Length
329 m
View 

Width: 1 in to maximum

Maximum Length

360 yd
View 
Width: 1 in to maximum
Maximum Available Width
48 in
Normal Slitting Tolerance
± 0.8 mm
Normal Slitting Tolerance
± 1/32 in
Core Size (ID)
76.2 mm
Core Size (ID)
3 in

Storage and Shelf Life

Product retains its performance and properties for 24 months from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% R.H. Storage in a plastic bag is recommended.

Recognition/Certification

MSDS: 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration’s Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

UL: Tapes 9442 and 9445 have been recognized by Underwriters Laboratories Inc. under Standard UL 969 Marking and Labeling in File MH26206. Tapes 9482PC and 9485PC have been recognized by Underwriters Laboratories Inc. under Standard UL 746C Polymeric Adhesives Systems, Electrical Equipment Component in File MH17478. If you require official recognition of any 350 adhesive under either UL 969 or UL 746C, please contact 3M-customer service at 1-800-362-3550.

For more information on the UL Certification, please visit the website at <http://www.3m.com/converter>, select UL Recognized Materials, and then select the specific product area.

Bottom Matter

3M
Industrial Adhesives and Tapes Division
3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-223-7427 or visit www.3m.com/converter. Address correspondence to: 3M

Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect unless in an agreement signed by the Technical Director of 3M’s Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer’s use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

Handling/Application Information

Application Examples

Ideal adhesive application temperature range is 70°F to 100°F (21°C to 38°C). Initial application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is satisfactory. For more specific information, contact our toll free 3M sales assistance number at 1-800-362-3550.

2 mil thick tapes may generally be used for joining materials that are relatively smooth, thin and have low residual stress. For materials with a rough or textured surface, the thicker adhesive film of the 5 mil tapes would be more appropriate for evaluation.

Application Techniques

For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Consult manufacturer’s Material Safety Data Sheet for proper handling and storage instructions. Bond strength can also be improved with firm application pressure and moderate heat (for metal surfaces only), from 100°F (38°C) to 130°F (54°C), causing the adhesive to develop intimate contact with the bonding surfaces.

References

Property Values
3m.com Product Page
https://www.3m.com/3M/en_US/p/d/b40065868/
Safety Data Sheet SDS
https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9482PC

Family Group

Link Tags:

- 9442

• 9445

• 9482PC

• 9485PC

• 9485EK

• 9675

Products	Adhesive Type	Liner	Liner Thickness	Total Tape Thickness (mm)	Short Term Temperature Resistance	Long Term Temperature Resistance	Minimum Long Term Temperature Resistance
9482PC	Acrylic	62# Polycoated Kraft	0.11 mm	0.05 mm	232 °C	250 °F	-40 °C

9485PC	Acrylic	62# Polycoated Kraft	0.11 mm	0.127 mm	232 °C	250 °F	-40 °C
9445	Acrylic	55# Densified Kraft	0.08 mm	0.127 mm	232 °C	250 °F	-40 °C
9675	Acrylic	83# Polycoated Kraft lay flat, tan with green "3M" print	0.16 mm	0.127 mm	232 °C	250 °F	-40 °C
9485EK	Acrylic	78# Extensible Polycoated Kraft	0.14 mm	0.127 mm	232 °C	250 °F	-40 °C
9442	Acrylic	55# Densified Kraft	0.08 mm	0.05 mm	232 °C	250 °F	-40 °C

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.