



Scotch-Weld™ DP410 Off-White

Product Data Sheet

Date: January 2013
Supersedes: October 2001

Product Description

DP410 epoxy adhesive is a low flow, two-part epoxy based structural adhesive. It is designed for use where toughness, high strength and rapid cure are required.

Key Features

- Rapid cure at room temperature; cure rate may be accelerated by the application of mild heat.
- Convenient 2:1 mix ratio by volume
- Mixed adhesive is low flow for ease of application
- Toughened epoxy system with good elevated temperature resistance
- Good environmental resistance

General Properties

	Base	Accelerator
Colour	Off-White	Off-White
Base	Toughened Epoxy	Modified Amine
Density (g/cm ³) (ISO 2811)	1.13	1.10
Consistency	Low Sagging Paste	Gel
Viscosity (ISO 2555)	70 PA.s	-
Mix Ratio <ul style="list-style-type: none">- by volume- by weight	100 100	50 48
Work Life (min) (ISO 10364)	12	12

Mechanical Properties

Overlap Shear Strength

Overlap shear specimens were made according to ISO 4587 using 1.6 mm thick clad aluminium 2024 T3
Surface prepared by the optimised FPL etch method.

Test Conditions (°C)	Results (MPa)
-55 ± 2	28
23 ± 2	38
85 ± 2	8

- Cure cycle : 7 days at 23 ± 2°C under a pressure of 100 kPa the first 24 hours
- Glass beads are used to control glue line thickness (# 150 µm)

Overlap Shear Strength on different substrates (ISO 4587)

Substrate	Result (MPa)
Abraded 2024 T3 clad aluminium	22
Abraded 6111 T6 aluminium	17
Cold rolled steel (abraded)	17
Brass (abraded)	16
Stainless Steel (abraded)	19
Polystyrene (abraded)	3
PVC	3
ABS	4
Polyamide 6.6	2
Glass Fibre Reinforced Polyester (abraded)	9 (substrate failure)
Glass Fibre Reinforced Phenolics	22 (substrate failure)
Carbon Fibre Reinforced Epoxy	33

- Cure cycle : 7 days at 23 ± 2°C under a pressure of 100 kPa the first 24 hours
- Glass beads are used to control glue line thickness (# 150 µm)


Peel Strength

Roller peel specimens were made according to ISO 4587 using 2024 T3 clad aluminium prepared by the optimised FPL etch

Metal to Metal (°C)	
23 ± 2	240 N/25 mm

Strength Build-Up

Typical results obtained on 1.6 mm thick FPL etched 2024 T3 clad aluminium.
Overlap shear specimens were made according to test method ISO 4587 with test speed 2.5 mm/min



Curing Time (Min)	OLs at 23°C (MPa)
10	0
30	0
50	0
60	0
70	0
75	0.36
80	1.50
90	3.07
120	12.08
150	18.05
180	22.70

- Cure cycle : 7 days at $23 \pm 2^\circ\text{C}$
- Glass beads are used to control glue line thickness (# 90 to 150 μm)

Directions for use

For high strength structural bonds, paint, oils, dust, mould release agents and other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental ageing resistance desired by user. For specific surface preparations on common substrates, see following information.

Use glove to minimise skin contact. Do not use solvents for cleaning hands

Mixing:

For Duo Pack Cartridges

DP 410 is supplied in a dual syringe plastic Duo-Pak cartridge as part of the EPX™ Applicator System. To use, simply insert the Duo-Pak cartridge into the EPX applicator and start plunging the cylinders using light pressure on the trigger. Next, remove the Duo-Pak cartridge cap and expel a small amount of adhesive to be sure both sides of the Duo-Pak cartridge are flowing evenly and freely. If automatic mixing of Part A and Part B is desired, attach the EPX mixing nozzle to the Duo-Pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after uniform colour is obtained.

Surface Preparation:

For high strength structural bonds, paint, oils, dust, mould release agents and other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental ageing resistance desired by user.

The following cleaning methods are suggested for common surfaces

Steel

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*
2. Sandblast or abrade using clean fine grit abrasive.
3. Wipe again with solvent to remove loose particles

Aluminium

1. Alkaline Degrease: Oakite 164 water solution (approx 10%) at $85 \pm 5^{\circ}\text{C}$ for 10-20 minutes. Rinse immediately in large quantities of cold running water.
2. Acid Etch : place panels in the following solution for 10 minutes at $65 \pm 3^{\circ}\text{C}$

- Sodium Dichromate 44.8g
- Sulphuric Acid, 66°Be 332g
- 2024-T3 aluminium
- (dissolved 1.5g
- Tap water adjust to 1 litre

3. Rinse panels in clean running tap water.
4. Air dry 15 minutes;
Force dry 10 minutes at $65 \pm 5^{\circ}\text{C}$
5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastic/Rubber

1. Wipe with Isopropyl alcohol.*
2. Abrade using fine grit abrasives.
3. Wipe with Isopropyl alcohol.*

Glass

1. Solvent wipe surface using acetone or MEK.*
2. Apply a thin coating (2.5 μm or less) of primer such as Scotch-Weld EC-3901 Primer to the glass surfaces to be bonded and allow the primer to dry before bonding.

() Note: When using solvents, extinguish all ignition sources and observe manufacturer's directions and precautions for handling such materials.*

Storage	Store 3M DP410 at room temperature or refrigerate for maximum shelf life. Rotate stock on a "first in-first out" basis.
Shelf Life	3M DP410 off-white has a shelf life of 12 months from date of dispatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity
Precautionary Information	Refer to product label and Material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office. www.3M.com

For Additional Information

To request additional product information or to arrange for sales assistance, call 0870 6080050 Address correspondence to: 3M United Kingdom PLC, 3M House, 28 Great Jackson Street, Manchester, M15 4PA

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of the 3M Company.

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA	Product Information : Tel 0870 60 800 50 Fax 0870 60 700 99	3M Ireland Limited The Iveagh Building The Park, Carrickmines Dublin 18, Ireland	Customer Service : Tel (01) 280 3555 Fax (01) 280 3509
--	---	--	--