



Scotch® Tape 8915

Performance Filament Tape

Manufactured in an ISO 9002 certified facility

Updated : June 2000
 Supersedes : February 1999

Product Description	A high performance transparent tape reinforced along its length with continuous glass yarn filaments which give the tape high tensile strength.	The transparent ScotchPro™ backing provides stiffness and excellent abrasion, moisture and scuff resistance. The pressure sensitive adhesive is specifically formulated to provide high adhesion, clean removability and stain resistance on most finishes.
----------------------------	---	---

Physical Properties

Not for specification purposes

Adhesive Type	Pressure sensitive hot melt solvent free (synthetic rubber resin)	
Backing	ScotchPro™ polypropylene film	
Reinforcement	Glass Yarn	
Thickness	150 microns (0.15 mm)	ASTM D-3652
Colour	Transparent; blue	
Available Widths	Contact your local sales office	Available Lengths Contact your local sales office
Core Size (ID)	76 mm (3")	
Storage Conditions	Store behind present stock, in a clean dry place. Temperature of 40 - 80°F (4-26°C) & 40-50 % Relative Humidity are recommended. Rotate your stock.	

Performance Characteristics

Not for specification purposes

Adhesion to Stainless Steel	6.5 N/cm	ASTM D-3330
Tensile Strength	298 N/cm	ASTM D-3759
Elongation at Break	3 %	ASTM D-3759

Date : June 2000
8915 Performance
Filament Tape

3M, Scotch and ScotchPro are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Packaging Systems Division

© 3M United Kingdom PLC 2000

3M ITALIA S.p.A.
Packaging Systems Customer Service
Via S. Bovio 3 - Milano S. Felice
20090 SEGRATE MI
ITALY

Tel. + 39 02 7035 3174/3173
Fax. + 39 02 7035 2104/3124